



Plastics Machinery Masterbatch Compound

MICROTEC srl
Via Croce Rossa, 42 - 35129 Padova
P.IVA: IT 03568000289
Sede Operativa: Via Po, 53/55
30030 Pianiga (VE), ITALY
Tel +39 0415190621 – Fax +39 0415194765
E-mail: info@microtecsrl.com



Micromaster[®]
Masterbatches

PRODUCT NAME : MICROMASTER[®] white 105

General Description

This product is designed for ease of dispersion and it is therefore suitable for direct addition and mixing with plastic resins, free from pollution problem caused by pigment.

Properties

Name	: MICROMASTER [®] white 105
Product Type	: White Masterbatch
Appearance	: Granule
Pellet Size	: 3x3 (± 0.3) mm
Pigment Content	: 50% \pm 3%
Filler	: yes
Carrier Resin	: LLDPE
Application	: Film blowing, blow moulding, injection moulding
Compatibility	: LDPE, HDPE, LLDPE, PP
Packaging	: 25 kgs/bag
Storage	: Keep at dry condition

The information contained in this Product Data Sheet relates only to the specific material designated herein and does not relate to use in combination with any other material or in any process. The information provided herein is based on technical data that Microtec believes to be reliable, however Microtec makes no representation or warranty as to the completeness or accuracy therefore and Microtec assumes no liability resulting from its use or for any claims, losses, or damages of any third party. Recipients receiving this information must exercise their own judgement as to the appropriateness of its use, and it is the user's responsibility to assess the material's suitability (including safety) for a particular purpose prior to such use.



Plastics Machinery Masterbatch Compound

MICROTEC srl
Via Croce Rossa, 42 - 35129 Padova
P.IVA: IT 03568000289
Sede Operativa: Via Po, 53/55
30030 Pianiga (VE), ITALY
Tel +39 0415190621 – Fax +39 0415194765
E-mail: info@microtecsrl.com

Technical Information

Classification Test Items	Test Method	Unit	Results
Melt Index (190°C/2160g)	ASTM D 1238	g/10 mins	15
Moisture Content	ASTM D 570	wt%	<0.2
Specific Gravity	ASTM D 792		1.98
Bulk Density		g/cm ³	1.20
Melting Point		°C	125
Heat Stability		°C	300
Heat Resistance		level	4-5
Let Down		%	1-5
Movability Resistance		level	5
Light Fastness		level	6-7

HEALTH AND SAFETY

Confirm with the European Resolution AP 89 (1) heavy metal content.

FOOD APPROVAL

MICROMASTER[®] white 105 can be used in food packaging according:

- European Union: EU Directive 10/2011 and EU Directive 2002/72/CE and the subsequent amendments; Directive 94/62/CE;
- ITALY: Decreto Ministeriale n. 34 del 21.03.1973 e successivi decreti applicativi;
- GERMANY: BgVO 10.04.1992, Ausgabe April 2003;
- France: J.O. de la Rèp. Francais 13.10.1992 – Brochure nr. 1227; et Arr du 02/01/2003.

REMARKS

PE – PP, for film colouring, bottles, drums, sheets, pipes, large garbage cans, food containers, trash and garbage bags, housewares etc.

The information contained in this Product Data Sheet relates only to the specific material designated herein and does not relate to use in combination with any other material or in any process. The information provided herein is based on technical data that Microtec believes to be reliable, however Microtec makes no representation or warranty as to the completeness or accuracy therefore and Microtec assumes no liability resulting from its use or for any claims, losses, or damages of any third party. Recipients receiving this information must exercise their own judgement as to the appropriateness of its use, and it is the user's responsibility to assess the material's suitability (including safety) for a particular purpose prior to such use.